

Aillen® Multilayer Ceramic Capacitors

1. DESCRIPTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

MLCC is made by NP0, X7R, X6S, X5R and Y5V dielectric material and which provides product with high electrical precision, stability and reliability.

2. FEATURES

- A wide selection of sizes is available (0201 to 1812).
- High capacitance in given case size.
- Capacitor with lead-free termination (pure Tin).

3. APPLICATIONS


- For general digital circuit.
- For power supply bypass capacitors.
- For consumer electronics.
- For telecommunication

4. HOW TO ORDER

1206	B	104	K	500	A	D
Size Inch (mm) 0201 (0603) 0402 (1005) 0603 (1608) 0805 (2012) 1206 (3216) 1210 (3225) 1812 (4532)	Dielectric N=NP0 (C0G) B=X7R Y=Y5V W=X5R S=X6S	Capacitance Two significant digits followed by no. of zeros. And R is in place of decimal point. eg.: 0R5=0.5pF 1R0=1.0pF 104=10x104=100nF	Tolerance A=±0.05pF B=±0.1pF C=±0.25pF D=±0.5pF F=±1% G=±2% J=±5% K=±10% M=±20% Z=-20/+80%	Rated Voltage Two significant digits followed by no. of zeros. And R is in place of decimal point. 4R0 =4 VDC 6R3 =6.3 VDC 100 =10 VDC 160 =16 VDC 250 =25 VDC 500 =50 VDC 101 =100 VDC	Thickness Item 5 & Item 7 for details	Packaging Quantity A: 1KPS/Reel B: 2KPS/Reel C: 3KPS/Reel D: 4KPS/Reel E: 15KPS/Reel I: 10KPS/Reel J: 2.5KPS/Reel F: others

Aillen® Multilayer Ceramic Capacitors

5. EXTERNAL DIMENSIONS



Size Inch(mm)	L (mm)	W (mm)	T(mm)/Symbol	Soldering Method	M _B (mm)	
0201 (0603)	0.6±0.09	0.30±0.09	0.30±0.09	L	R	0.15±0.1/-0.05
0402 (1005)	1.00±0.20	0.50±0.20	0.50±0.20	H	R	0.25±0.05/-0.10
0603 (1608)	1.60±0.20	0.80±0.20	0.50±0.20	H	R/W	0.40±0.15
			0.80±0.10	S	R/W	
			0.80±0.20	X	R/W	
0805 (2012)	2.00±0.20	1.25±0.20	0.50±0.20	H	R	0.50±0.20
			0.60±0.10	A	R/W	
			0.80±0.20	X	R/W	
			0.85±0.15	B	R/W	
			1.25±0.20	C	R	
1206 (3216)	3.20±0.30	1.60±0.30	0.85±0.15	B	R/W	0.60±0.20 0.50±0.25
			0.95±0.10	I	R	
			1.25±0.20	C	R	
			1.15±0.20	J	R	
1210 (3225)	3.20±0.40	3.20±0.40	0.95±0.10	I	R	0.75±0.25
			0.85±0.10	T	R	
			1.25±0.20	C	R	
			1.60±0.20	E	R	
			2.00±0.20	F	R	
			2.50±0.30	Y	R	
1808 (4520)	4.50±0.40	2.03±0.25	1.25±0.20	C	R	0.75±0.25 0.50±0.25*
			1.40±0.20	J	R	
			1.60±0.20	E	R	
			2.00±0.20	F	R	
1812 (4532)	4.50±0.40	3.20±0.40	1.25±0.20	C	R	0.75±0.25 0.50±0.25*
			1.60±0.20	E	R	
			2.00±0.20	F	R	
			2.50±0.30	Y	R	
			2.80±0.30	P	R	
1825 (4563)	4.50±0.40	6.30±0.40	1.60±0.20	D	R	0.75±0.35
			2.00±0.20	K	R	0.85±0.35
			2.50±0.30	M	R	0.85±0.35
			2.80±0.30	U	R	0.85±0.35
2211(5728)	5.70±0.40	2.80±0.30	1.60±0.20	D	R	0.75±0.35
			2.00±0.20	K	R	0.85±0.35
			2.50±0.30	M	R	0.85±0.35
			2.80±0.30	U	R	0.85±0.35
2220(5750)	5.70±0.40	5.00±0.40	1.60±0.20	D	R	0.75±0.35
			2.00±0.20	K	R	0.85±0.35
			2.50±0.30	M	R	0.85±0.35
			2.80±0.30	U	R	0.85±0.35
2225(5763)	5.70±0.40	6.30±0.40	1.60±0.20	D	R	0.75±0.35
			2.00±0.20	K	R	0.85±0.35
			2.50±0.30	M	R	0.85±0.35
			2.80±0.30	U	R	0.85±0.35

*For 1206_≥1000V, 1808/1812_{200V~4000V} and safety certificated products.

Aillen® Multilayer Ceramic Capacitors

6. GENERAL ELECTRICAL DATA

Dielectric	NP0	X7R	Y5V	X5R	X6S	X7S
Size	0201, 0402, 0603, 0805, 1206, 1210, 1812					
Capacitance range*	0.1pF to 0.1μF	100pF to 47μF	0.01μF to 100μF	100pF to 220μF	0.1μF to 100μF	1μF to 100μF
Capacitance tolerance**	Cap≤5pF ^{#1} : A (±0.05pF), B (±0.1pF), C (±0.25pF) 5pF<Cap<10pF: C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%), K (±10%)	J (±5%), K (±10%), M (±20%)	M (±20%), Z (-20/+80%)	K (±10%), M (±20%)	K (±10%), M (±20%)	K (±10%), M (±20%)
Rated voltage (WVDC)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 50V, 100V				
Operating temperature	-55 to +125°C		-25 to +85°C	-55 to +85°C	-55 to +105°C	-55 to +125°C
Capacitance characteristic	±30ppm	±15%	+30/-80%	±15%	±22%	±22%
Termination	Ni/Sn (lead-free termination)					

#1: NP0, 0.1pF product only provide B tolerance; 0603N0R4 provide B&C tolerance; 0603N0R3 only provide C tolerance.

* Measured at the condition of 30~70% related humidity.

NP0: Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2Vrms, 1.0kHz±10% for Cap>1000pF, 25°C at ambient temperature

X7R/X6S/X5R/X7S: Please refer to page 13 "Reliability test conditions and requirements" for detail.

Y5V: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 20°C ambient temperature.

** Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour and then leave in ambient condition for 24±2 hours before measurement.

X7R:

Note 1:

X5R:

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 100V	≤ 2.5%	≤ 3% 1206 ≥ 0.47μF
		≤ 5% 0603 ≥ 0.068μF; 0805 > 0.1μF; 1206 ≥ 1μF; 1210 ≥ 2.2μF;
		≤ 10% 0805 > 0.22μF; 1210 ≥ 3.3μF
50V	≤ 2.5%	≤ 3% 0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF
		≤ 10% 0402 ≥ 0.012μF; 0603 > 0.1μF; 0805/X7R > 0.47μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF;
35V	≤ 3.5%	≤ 10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF
25V	≤ 3.5%	≤ 5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210/X7R ≥ 10μF
		≤ 7% 0603 ≥ 0.33μF
		≤ 10% 0201 ≥ 0.1μF; 0402/X7R ≥ 0.056μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
16V	≤ 3.5%	≤ 12.5% 0402 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF
		≤ 10% 0201/X7R ≥ 0.022μF; 0402 ≥ 0.22μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
10V	≤ 5%	≤ 10% 0201 ≥ 0.012μF; 0402 ≥ 0.22μF; 0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF; 01R5/X5R
		≤ 15% 0201 ≥ 0.1μF; 0402 ≥ 1μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 1μF; 0603 ≥ 10μF; 0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μF;
6.3V	≤ 10%	≤ 20% 0402 ≥ 2.2μF
		≤ 15% ---
4V	≤ 15%	---

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 100V	≤ 2.5%	≤ 3% 1206 ≥ 0.47μF
		≤ 5% 0603 ≥ 0.068μF; 0805 > 0.1μF; 1206 ≥ 1μF; 1210 ≥ 2.2μF;
		≤ 10% 0805 > 0.22μF; 1210 ≥ 3.3μF
50V	≤ 2.5%	≤ 3% 0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF
		≤ 10% 0402 ≥ 0.012μF; 0603 > 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF;
35V	≤ 3.5%	≤ 10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF
25V	≤ 3.5%	≤ 5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210/X7R ≥ 10μF
		≤ 7% 0603 ≥ 0.33μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210/X5R ≥ 10μF;
16V	≤ 3.5%	≤ 12.5% 0402 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
10V	≤ 5%	≤ 10% 0201 ≥ 0.012μF; 0402 ≥ 0.22μF; 0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF;
		≤ 15% 0201 ≥ 0.1μF; 0402 ≥ 1μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 1μF; 0603 ≥ 10μF; 0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μF;
6.3V	≤ 10%	≤ 20% 0402 ≥ 2.2μF
		≤ 15% ---
4V	≤ 15%	---

Y5V:

X6S:

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 50V	≤ 5%	≤ 7% 0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF;
		≤ 12.5% 1210 ≥ 6.8μF
35V	≤ 7%	---
25V	≤ 5%	≤ 7% 0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF
		≤ 9% 0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
16V (C<1.0μF)	≤ 7%	≤ 9% 0402 ≥ 0.068μF; 0603 ≥ 0.68μF
16V (C≥1.0μF)	≤ 9%	≤ 12.5% 0402 ≥ 0.22μF
10V	≤ 12.5%	0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF;
6.3V	≤ 20%	0402 ≥ 0.47μF

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 100V	≤ 2.5%	≤ 3% 1206 ≥ 0.47μF
		≤ 5% 0603 ≥ 0.068μF; 0805 > 0.1μF; 1206 ≥ 1μF; 1210 ≥ 2.2μF;
		≤ 10% 0805 > 0.22μF; 1210 ≥ 3.3μF
50V	≤ 2.5%	≤ 3% 0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF
		≤ 10% 0402 ≥ 0.012μF; 0603 > 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF;
35V	≤ 3.5%	≤ 10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF
25V	≤ 3.5%	≤ 5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210/X7R ≥ 10μF
		≤ 7% 0603 ≥ 0.33μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
16V	≤ 3.5%	≤ 12.5% 0402 ≥ 0.47μF
		≤ 5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF;
10V	≤ 5%	≤ 10% 0201 ≥ 0.012μF; 0402 ≥ 0.22μF; 0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF;
		≤ 15% 0201 ≥ 0.1μF; 0402 ≥ 1μF
		≤ 10% 0201 ≥ 0.1μF; 0402/X6S ≥ 0.47μF; 0603 ≥ 10μF; 0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μF;
6.3V	≤ 10%	≤ 20% 0402 ≥ 2.2μF
		≤ 15% ---
4V	≤ 15%	---

Aillen® Multilayer Ceramic Capacitors

7. CAPACITANCE RANGE

7-1. NP0 Dielectric 0201, 0402, 0603, 0805 Sizes

DIELECTRIC		NP0																		
SIZE		0201			0402				0603					0805						
RATED VOLTAGE (VDC)		16	25	50	10	16	25	50	100	10	16	25	50	100	10	16	25	50	100	
Capacitance	0.1pF (0R1)	L	L	L	E	E	E	E												
	0.2pF (0R2)	L	L	L	E	E	E	E												
	0.3pF (0R3)	L	L	L	E	E	E	E												
	0.4pF (0R4)	L	L	L	E	E	E	E												
	0.5pF (0R5)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	0.6pF (0R6)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	0.7pF (0R7)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	0.8pF (0R8)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	0.9pF (0R9)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	1.0pF (1R0)	L	L	L	E	E	E	E	E	X	X	X	X	X						
	1.2pF (1R2)																			
	1.5pF (1R5)																			
	1.8pF (1R8)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	2.0pF (2R0)	L	L	L	H	H	H	H	H											
	2.2pF (2R2)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	2.7pF (2R7)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	3.0pF (3R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	3.3pF (3R3)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	3.9pF (3R9)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	4.0pF (4R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	4.7pF (4R7)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	5.0pF (5R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	5.6pF (5R6)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	6.0pF (6R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	6.8pF (6R8)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	7.0pF (7R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	8.0pF (8R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	8.2pF (8R2)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	9.0pF (9R0)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	10pF (100)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	12pF (120)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	15pF (150)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	18pF (180)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	22pF (220)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	27pF (270)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	33pF (330)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	39pF (390)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	47pF (470)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	56pF (560)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	68pF (680)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	82pF (820)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
	100pF (101)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A	
120pF (121)	L	L	L	H	H	H	H	H	S	S	S	S	S	A	A	A	A	A		
150pF (151)				H	H	H	H	H	S	S	S	S	S	A	A	A	A	A		
180pF (181)				H	H	H	H	H	S	S	S	S	S	A	A	A	A	A		
220pF (221)				H	H	H	H	H	S	S	S	S	S	A	A	A	A	A		
270pF (271)				H	H	H	H		S	S	S	S	S	A	A	A	A	A		
330pF (331)				H	H	H	H		S	S	S	S	S	A	A	A	A	A		
390pF (391)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
470pF (471)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
560pF (561)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
680pF (681)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
820pF (821)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
1,000pF (102)				H	H	H	H		S	S	S	S	S	B	B	B	B	B		
1,200pF (122)									X	X	X	X	X	B	B	B	B	B		
1,500pF (152)									X	X	X	X	X	B	B	B	B	B		
1,800pF (182)									X	X	X	X		B	B	B	B	B		
2,200pF (222)									X	X	X	X		B	B	B	B	B		
2,700pF (272)									X	X	X	X		C	C	C	C	C		
3,300pF (332)									X	X	X	X		C	C	C	C	C		
3,900pF (392)									X	X	X	X		C	C	C	C	C		
4,700pF (472)									X	X	X	X		C	C	C	C	C		
5,600pF (562)									X	X	X	X		C	C	C	C	C		
6,800pF (682)									X	X	X	X		C	C	C	C	C		
8,200pF (822)									X	X	X	X		C	C	C	C	C		
0.010μF (103)									X	X	X	X		C	C	C	C			
0.012μF (123)														T	T	T	T			
0.018μF (183)														C	C	C	C			
0.022μF (223)														C	C	C	C			

1、 The letter in cell is expressed the symbol of product thickness.

2、 For more information about products with special capacitance or other data, please contact our sales local representative.

Aillen® Multilayer Ceramic Capacitors

7-1. NP0 Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC		NP0													
SIZE		1206					1210					1812			
RATED VOLTAGE(VDC)		10	16	25	50	100	10	16	25	50	100	16	50	100	
Capacitance	1.0pF (1R0)														
	1.2pF (1R2)	B	B	B	B	B									
	1.5pF (1R5)	B	B	B	B	B									
	1.8pF (1R8)	B	B	B	B	B									
	2.2pF (2R2)	B	B	B	B	B									
	2.7pF (2R7)	B	B	B	B	B									
	3.3pF (3R3)	B	B	B	B	B									
	3.9pF (3R9)	B	B	B	B	B									
	4.7pF (4R7)	B	B	B	B	B									
	5.6pF (5R6)	B	B	B	B	B									
	6.8pF (6R8)	B	B	B	B	B									
	8.2pF (8R2)	B	B	B	B	B									
	10pF (100)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	15pF (150)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	18pF (180)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	22pF (220)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	27pF (270)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	33pF (330)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	39pF (390)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	47pF (470)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	56pF (560)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	68pF (680)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	82pF (820)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	100pF (101)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	120pF (121)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	150pF (151)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	180pF (181)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	220pF (221)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	270pF (271)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	330pF (331)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	390pF (391)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	560pF (561)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	680pF (681)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	820pF (821)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	1,000pF (102)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	1,200pF (122)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	1,500pF (152)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	1,800pF (182)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	2,200pF (222)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	2,700pF (272)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	3,300pF (332)	B	B	B	B	B	I	I	I	I	I	C	C	C	
	3,900pF (392)	B	B	B	B	B	I	I	I	I	I	C	C	C	
4,700pF (472)	B	B	B	B	B	I	I	I	I	I	C	C	C		
5,600pF (562)	B	B	B	B	B	I	I	I	I	I	C	C	C		
6,800pF (682)	I	I	I	I	I	I	I	I	I	I	C	C	C		
8,200pF (822)	C	C	C	C	C	I	I	I	I	I	C	C	C		
0.010μF (103)	C	C	C	C	C	I	I	I	I	I	C	C	C		
0.012μF (123)	T/P	T/P	T/P	T/P	T/P	C	C	C	C	C	C	C	C		
0.015μF (153)	T/P	T/P	T/P	T/P	T/P	C	C	C	C	C	C	C	C		
0.018μF (183)	T/P	T/P	T/P	T/P	T/P		K	K	K	K	C	C	C		
0.022μF (223)	T/P	T/P	T/P	T/P	T/P		K	K	K	K	C	C	C		
0.027μF (273)	T/P	T/P	T/P	T/P			K	K	K	K	C	C	C		
0.033μF (333)	T/P	T/P	T/P	T/P			K	K	K	K	C	C	C		
0.039μF (393)	J	J	J	J			K	K	K	K	M	M	M		
0.047μF (473)	J	J	J	J			K	K	K	K	M	M	M		
0.056μF (563)	J	J	J	J							M	M	M		
0.068μF (683)	D	D	D	D							M	M	M		
0.082μF (823)	D	D	D	D							M	M	M		
0.1μF (104)	D	D	D	D							M	M	M		

1、 The letter in cell is expressed the symbol of product thickness.

2、 For more information about products with special capacitance or other data, please contact our sales local representative.

Aillen® Multilayer Ceramic Capacitors

7-2. X7R Dielectric 0201, 0402, 0603, 0805 Sizes

DIELECTRIC		X7R																												
SIZE		0201					0402					0603						0805												
RATED VOLTAGE(VDC)		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	50	100
Capacitance	100pF (101)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	120pF (121)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	150pF (151)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	180pF (181)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	220pF (221)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	270pF (271)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	330pF (331)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	390pF (391)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	470pF (471)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	560pF (561)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	680pF (681)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	820pF (821)			L	L	L	H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	1,000pF (102)	L	L	L	L	L	H	H	H	H	H	H	S	S	S	S	S	S/B	B	B	B	B	B	B	B	B	B	B		
	1,200pF (122)	L	L	L	L		H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	1,500pF (152)	L	L	L	L		H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	1,800pF (182)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	2,200pF (222)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	2,700pF (272)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	3,300pF (332)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	3,900pF (392)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	4,700pF (472)	L	L	L			H	H	H	H	H	H	S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	5,600pF (562)	L	L				H	H	H	H	H		S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	6,800pF (682)	L	L				H	H	H	H	H		S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	8,200pF (822)	L	L				H	H	H	H	H		S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	0.010μF (103)	L	L	L			H	H	H	H	H		S	S	S	S	S	S	B	B	B	B	B	B	B	B	B	B		
	0.012μF (123)						H	H	H	H			S	S	S	S	S	X	B	B	B	B	B	B	B	B	B	B		
	0.015μF (153)						H	H	H	H			S	S	S	S	S	X	B	B	B	B	B	B	B	B	B	B		
	0.018μF (183)						H	H	H	H			S	S	S	S	S	X	B	B	B	B	B	B	B	B	B	B		
	0.022μF (223)						H	H	H	H	H		S	S	S	S	S	X	B	B	B	B	B	B	B	B	B	B		
	0.027μF (273)						H	H	H	H	H		S	S	S	S	S	X	B	B	B	B	B	B	B	B	B	C		
	0.033μF (333)						H	H	H	H	H		S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C		
	0.039μF (393)						H	H	H	H			S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C		
	0.047μF (473)						H	H	H	H	H		S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C		
0.056μF (563)						H	H	H				S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C			
0.068μF (683)						H	H	H		H		S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C			
0.082μF (823)						H	H	H				S	S	S	S	X	X	B	B	B	B	B	B	B	B	B	C			
0.10μF (104)						H	H	H	H	H		S	S	S/B	S	X	X	B	B	B	B	B	B	B	B	B	C			
0.12μF (124)												S	S	S	X			B	B	B	C	C	C	C	C	C				
0.15μF (154)												S	S	S	X			C	C	C	C	C	C	C	C	C				
0.18μF (184)												S	S	S	X			C	C	C	C	C	C	C	C	C				
0.22μF (224)						H	H	H	H			S	S	S	X	X		C	C	C	C	C	C	C	C	C				
0.27μF (274)												X	X	X	X			C	C	C	C	C	C	C	C	C				
0.33μF (334)												X	X	X	X			C	C	C	C	C	C	C	C	C				
0.39μF (394)												X	X	X	X			C	C	C	C	C	C	C	C	C				
0.47μF (474)						H	H					X	X	X	X	X		C	C	C	C	C	C	C	C	C				
0.56μF (564)												X	X	X				C	C	C	C									
0.68μF (684)												X	X	X				C	C	C	C									
0.82μF (824)												X	X	X				C	C	C	C									
1.0μF (105)						H	H					X	X	X	X	X		C	C	C	C	C	C							
1.5μF (155)																		C	C	C	C	C								
2.2μF (225)												X	X	X				C	C	C	C	C								
3.3μF (335)																														
4.7μF (475)												X	X	X				C	C	C	C									
6.8μF (685)																														
10μF (106)																		C*	C*	C*										
22μF (226)																														

- 1、 The letter in cell is expressed the symbol of product thickness.
- 2、 The letter in cell with “*” mark is expressed product not in 20% (code “M”) tolerance.

Aillen® Multilayer Ceramic Capacitors

7-2. X7R Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC	X7R																	
	SIZE	1206					1210					1812						
RATED VOLTAGE(VDC)	6.3	10	16	25	50	100	6.3	10	16	25	50	100	10	16	25	50	100	
Capacitance	100pF (101)																	
	120pF (121)																	
	150pF (151)		B	B	B	B	B											
	180pF (181)		B	B	B	B	B											
	220pF (221)		B	B	B	B	B											
	270pF (271)		B	B	B	B	B											
	330pF (331)		B	B	B	B	B											
	390pF (391)		B	B	B	B	B											
	470pF (471)		B	B	B	B	B											
	560pF (561)		B	B	B	B	B											
	680pF (681)		B	B	B	B	B											
	820pF (821)		B	B	B	B	B											
	1,000pF (102)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	1,200pF (122)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	1,500pF (152)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	1,800pF (182)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	2,200pF (222)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	2,700pF (272)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	3,300pF (332)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	3,900pF (392)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	4,700pF (472)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	5,600pF (562)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	6,800pF (682)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	8,200pF (822)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.010μF (103)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.012μF (123)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.015μF (153)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.018μF (183)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.022μF (223)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.027μF (273)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.033μF (333)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.039μF (393)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.047μF (473)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.056μF (563)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.068μF (683)		B	B	B	B	B	I	I	I	I	I	I	C	C	C	C	C
	0.082μF (823)		B	B	B	B	C	I	I	I	I	I	I	C	C	C	C	C
	0.10μF (104)		B	B	B	B	C	I	I	I	I	I	I	C	C	C	C	C
	0.12μF (124)		B	B	B	B	C	I	I	I	I	I	I	C	C	C	C	C
	0.15μF (154)		I	I	I	I	D	I	I	I	I	I	C	C	C	C	C	C
	0.18μF (184)		I	I	I	I	D	I	I	I	I	I	C	C	C	C	C	C
0.22μF (224)		I	I	I	I	D	I	I	I	I	I	C	C	C	C	C	C	
0.27μF (274)		I	I	I	C	D	I	I	I	I	D	C	C	C	C	C	C	
0.33μF (334)		I	I	I	C	D	I	I	I	C	D	C	C	C	C	C	C	
0.39μF (394)		I	I	J	P	D	I	I	I	C	M	C	C	C	C	C	C	
0.47μF (474)		J	J	J	P	D	I	I	I	C	M	C	C	C	C	C	K	
0.56μF (564)		J	J	J	P	P	C	C	C	C	M	C	C	C	C	C	K	
0.68μF (684)		J	J	J	P	P	C	C	C	C	K	C	C	C	C	K	K	
0.82μF (824)		J	J	J	P	P	C	C	C	C	K	C	C	C	C	K	K	
1.0μF (105)		J	J	J	P	P	C	C	C	C	K	C	C	C	C	K	K	
1.5μF (155)	J	J	J	P					K	D	M	M					K	
2.2μF (225)	J	J	J	P	P	P			K	D	M	M				M	M	
3.3μF (335)		P	P	P	P				K	D								
4.7μF (475)	P	P	P	P	P				K	K	K	M						
6.8μF (685)																		
10μF (106)	P	P	P	P					K	K	K	M						
22μF (226)	P*	P*	P*						M	M	M							
47μF (476)							M	M										
100μF (107)																		

- 1、 The letter in cell is expressed the symbol of product thickness.
- 2、 The letter in cell with “*” mark is expressed product not in 20% (code “M”) tolerance.

Aillen® Multilayer Ceramic Capacitors

7-3. Y5V Dielectric 0402, 0603, 0805 Sizes

DIELECTRIC		Y5V															
SIZE		0402					0603					0805					
RATED VOLTAGE(VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	100
Capacitance	0.010μF (103)		H	H	H	H		S	S	S	S		A	A	A	A	B
	0.015μF (153)		H	H	H	H		S	S	S	S		A	A	A	A	B
	0.022μF (223)		H	H	H	H		S	S	S	S		A	A	A	A	B
	0.033μF (333)		H	H	H	H		S	S	S	S		A	A	A	A	B
	0.047μF (473)		H	H	H			S	S	S	S		A	A	A	A	B
	0.068μF (683)		H	H	H			S	S	S	S		A	A	A	A	B
	0.10μF (104)		H	H	H			S	S	S	S		A	A	A	A	B
	0.15μF (154)		H	H	H			S	S	S	S		A	A	A	A	
	0.22μF (224)	H	H	H				S	S	S	S		A	A	A	A	
	0.33μF (334)	H	H	H				S	S	S	X		B	B	B	B	
	0.47μF (474)	H	H	H				S	S	X	X		B	B	B	B	
	0.68μF (684)	H						S	X	X			B	B	C	C	
	1.0μF (105)	H	H					S	X	X			B	B	C	C	
	1.5μF (155)							S					C	C			
	2.2μF (225)						S	S	X				C	C	C		
	3.3μF (335)												C	C			
	4.7μF (475)						X	X					C	C	C		
6.8μF (685)												C					
10μF (106)												C	C	C			
22μF (226)												C	C				

7-3. Y5V Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC		Y5V																		
SIZE		1206					1210					1812								
RATED VOLTAGE(VDC)		6.3	10	16	25	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100	
Capacitance	0.010μF (103)		B	B	B	B	B							I					C	
	0.015μF (153)		B	B	B	B	B							I					C	
	0.022μF (223)		B	B	B	B	B							I					C	
	0.033μF (333)		B	B	B	B	B							I					C	
	0.047μF (473)		B	B	B	B	B							I					C	
	0.068μF (683)		B	B	B	B	B							I					C	
	0.10μF (104)		B	B	B	B	B		I	I	I			I	I	C	C	C	C	C
	0.15μF (154)		B	B	B	B	I		I	I	I			I	I	C	C	C	C	C
	0.22μF (224)		B	B	B	B	I		I	I	I			I	I	C	C	C	C	C
	0.33μF (334)		B	B	B	B			I	I	I			I	I	C	C	C	C	C
	0.47μF (474)		B	B	B	B			I	I	I			I		C	C	C	C	C
	0.68μF (684)		B	B	B	B			I	I	I			I		C	C	C	C	C
	1.0μF (105)		I	I	I	I			I	I	I			I		C	C	C	C	C
	1.5μF (155)		I	I	I				I	I	I					C	C	C	C	
	2.2μF (225)		I	I	I	J			I	I	I			D		C	C	C	C	
	3.3μF (335)		J	J	J				I	I	I					C	C	C	C	
	4.7μF (475)		J	J	J	P			I	I	C			D		C	C	C	C	
6.8μF (685)		J	J					I	I	C			K		C	C	C	C		
10μF (106)		J	J	P				C	C	D		K	K		C	C	C	K		
22μF (226)		P	P					K	K											
47μF (476)	P							K	K							M				
100μF (107)								M												

- 1、 The letter in cell is expressed the symbol of product thickness.
- 2、 For more information about products with special capacitance or other data, please contact our sales local representative.

Aillen® Multilayer Ceramic Capacitors

7-4. X5R Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes

Dielectric		X5R														
Size		0201					0402					0603				
Rated Voltage (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50
Capacitance	100pF (101)			L	L	L										
	120pF (121)			L	L	L										
	150pF (151)			L	L	L										
	180pF (181)			L	L	L										
	220pF (221)			L	L	L										
	270pF (271)			L	L	L										
	330pF (331)			L	L	L										
	390pF (391)			L	L	L										
	470pF (471)			L	L	L										
	560pF (561)			L	L	L										
	680pF (681)			L	L	L										
	820pF (821)			L	L	L										
	1,000pF (102)		L	L	L	L										
	1,500pF (152)		L	L												
	2,200pF (222)		L	L												
	2,700pF (272)		L	L												
	3,300pF (332)		L	L												
	4,700pF (472)		L	L												
	6,800pF (682)		L													
	0.010µF (103)	L	L	L	L											
	0.015µF (153)	L	L													
	0.022µF (223)	L	L													
	0.027µF (273)	L	L						H							
	0.033µF (333)	L	L						H							
	0.039µF (393)	L	L						H							
	0.047µF (473)	L	L						H							
	0.056µF (563)	L	L						H	H						
	0.068µF (683)	L	L						H	H						
	0.082µF (823)	L	L					H	H	H						
	0.10µF (104)	L	L	L	L		H	H	H	H	H					
	0.15µF (154)						H	H	H	H						
	0.22µF (224)	L	L				H	H	H	H	H			X	X	
0.27µF (274)												X	X	X	X	
0.33µF (334)						H	H				X	X	X	X		
0.39µF (394)												X	X	X	X	
0.47µF (474)	L					H	H	E	E	E	X	X/B	X	X	X	
0.68µF (684)						H	H				X	X	X	X		
0.82µF (824)											X	X	X			
1.0µF (105)	L*	L*	L*			H	H	H	H		X	X	X	X/B	X	
1.5µF (155)											X					
2.2µF (225)	L*	L*				H	H	E	E		X	X	X	X	X	
3.3µF (335)											X	X				
4.7µF (475)						E*	E*	E*			X	X	X	X		
6.8µF (685)																
10µF (106)						E*	E*				X	X	X	X*		
22µF (226)											X*	X*				

Dielectric		X5R																
Size		0805					1206					1210						
Rated Voltage (VDC)		4	6.3	10	16	25	50	6.3	10	16	25	50	4	6.3	10	16	25	50
Capacitance	1.0µF (105)			C	C	C	C											
	1.5µF (155)		C	C	C	C		J	J					K	K			
	2.2µF (225)		C	C	C	C	C	J	J	P	P			K	K			
	3.3µF (335)		C	C	C	C		P	P	P								
	4.7µF (475)		C	C	C	C	C	P	P	P	P	P			K	K	K	
	6.8µF (685)							P	P									
	10µF (106)		C	C	C	C	C	P	P	P	P	P		K	K	K	K	M
	22µF (226)		C	C*	C*	C*		P	P	P	P			M	M	M	M	
	47µF (476)		C*	C*				P	P					M	M	M		
	100µF (107)	C*						P*						M*	M*			
	220µF (227)												M*					

- 1、The letter in cell is expressed the symbol of product thickness.
- 2、The letter in cell with “*” mark is expressed product not in 20% (code “M”) tolerance.

Aillen® Multilayer Ceramic Capacitors

7-5. X6S Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes

Dielectric		X6S																																
Size		0201					0402					0603					0805					1206					1210							
Rated Voltage (VDC)		4	6.3	6.3	10	16	25	4	6.3	10	16	25	4	6.3	10	16	25	50	4	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50
Capacitance	0.10μF (104)	L	L																															
	0.15μF (154)																																	
	0.22μF (224)		L																															
	0.33μF (334)																																	
	0.47μF (474)			H																														
	0.68μF (684)																																	
	1.0μF (105)	L*		H	E	E	E																											
	1.5μF (155)																																	
	2.2μF (225)			H	E	E						X																						
	3.3μF (335)																																	
	4.7μF (475)										X		X	X									C	C										
	6.8μF(685)																																	
	10μF (106)										X*	X*	X*						C	C	C	C	C					D						
	22μF (226)									X*	X*										C*	C*	C*					P	P*				M	
47μF (476)																				C*							P					M		
100μF (107)																																M*		

- 1、The letter in cell is expressed the symbol of product thickness.
- 2、The letter in cell with “*” mark is expressed product not in 20% (code “M”) tolerance.

8. PACKAGING STYLE AND QUANTIT

Unit: pieces

Size	Thickness (mm)/Symbol		Paper tape		Plastic tape	
			7" reel	13" reel	7" reel	13" reel
0201 (0603)	0.30±0.03	L	15,000	70,000	-	-
	0.30±0.05	L	15,000	-	-	-
	0.30±0.09	L	15,000	-	-	-
0402 (1005)	0.50±0.05	H	10,000	50,000	-	-
	0.50+0.02/-0.05	Q	10,000	50,000	-	-
	0.50±0.20	E	10,000	-	-	-
0603 (1608)	0.50±0.10	N	4,000	-	-	-
	0.80±0.07	S	4,000	15,000	-	-
	0.80+0.15/-0.10	X	4,000	15,000	-	-
0805 (2012)	0.50±0.10	N	4,000	15,000	-	-
	0.60±0.10	A	4,000	15,000	-	-
	0.85±0.15	B	4,000	15,000	-	-
	0.85±0.10	T	4,000	15,000	-	-
1206 (3216)	1.25±0.15	C	-	-	3,000	10,000
	0.85±0.15	B	4,000	15,000	-	-
	0.85±0.10	T	4,000	15,000	-	-
	0.95±0.10	I	-	-	3,000	10,000
	1.15±0.15	J	-	-	3,000	10,000
	1.25±0.15	C	-	-	3,000	10,000
1210 (3225)	1.60±0.15	D	-	-	2,000	10,000
	1.60+0.30/-0.10	P	-	-	2,000	9,000
	0.85±0.10	T	-	-	3,000	10,000
	0.95±0.10	I	-	-	3,000	10,000
	1.25±0.15	C	-	-	3,000	10,000
	1.60±0.15	D	-	-	2,000	-
1808 (4520)	2.00±0.20	K	-	-	1,000	6,000
	2.50±0.30	M	-	-	1,000	6,000
	1.25±0.15	C	-	-	2,000	10,000
	1.10±0.15	F	-	-	2,000	10,000
	1.60±0.15	D	-	-	2,000	8,000
1812 (4532)	2.00±0.20	K	-	-	1,000	6,000
	1.25±0.15	C	-	-	1,000	5,000
	1.60±0.15	D	-	-	1,000	-
	2.00±0.20	K	-	-	1,000	-
	2.50±0.30	M	-	-	500	3,000
2.80±0.30	U	-	-	500	-	

9. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																																				
1	Visual and Mechanical	---	* No remarkable defect. * Dimensions to conform to individual specification sheet.																																																				
2	Capacitance	Class I: (NP0) ≤ 1000pF, 1.0±0.2Vrms · 1MHz±10% > 1000pF, 1.0±0.2Vrms · 1KHz±10% Class II: (X7R, X6S, X5R, Y5V) C ≤ 10μF, 1.0±0.2Vrms · 1KHz±10% ** C > 10μF, 0.5±0.2Vrms · 120Hz±20% ** Test condition: 0.5±0.2Vrms · 1KHz±10%	* Shall not exceed the limits given in the detailed spec.																																																				
3	Q/D.F.(Dissipation Factor)	X7R: 0805=106(6.3V), 0603/475(6.3V) X5R: 0201 ≥ 224 (6.3V,10V,16V) #1 0402 ≥ 475 (6.3V,16V), 0402 ≥ 225(10V), 0603=106 (6.3V,10V), TT18X ≥ 475(10V) , TT15X series X6S: 0201/474(4V),0201 ≥ 104 (6.3V,10V)#1 0402 ≥ 225 (6.3V), 0402/475 (10V), 0603/106 (6.3V), #1 Excluding X5R/0201/105(6.3V);225(10V), X6S/0201/104(10V) (1.0±0.2Vrms · 1KHz±10%) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr for 24±2 hrs at room temp.	NP0: Cap≥30pF, Q≥1000; Cap<30pF,Q≥400+20C X7R,X5R,X6S,Y5V:See <Note 1>																																																				
4	Dielectric Strength	* To apply voltage (≤100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	* No evidence of damage or flash over during test.																																																				
5	Insulation Resistance	* Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement. To apply rated voltage for max. 120 sec.	Class I: (NP0) 10GΩ or RxC≥500Ω·F whichever is smaller. Class II (X7R, X5R, X6S, Y5V) <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>IR</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="5">10GΩ or RxC≥100Ω·F whichever is smaller</td> </tr> <tr> <td>50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF</td> </tr> <tr> <td>35V:0805≥2.2μF;1206≥2.2μF;1210≥10μF</td> </tr> <tr> <td>25V:0402≥1μF;0603≥2.2μF;0805≥2.2μF;1206≥10μF;1210≥10μF</td> </tr> <tr> <td>16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF</td> </tr> <tr> <td>10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF;1206≥4.7μF;1210≥47μF</td> <td rowspan="5">RxC≥50Ω·F.</td> </tr> <tr> <td>6.3V ; 4V</td> </tr> <tr> <td>All X6S items</td> </tr> <tr> <td>100V: 1210≥3.3μF</td> </tr> <tr> <td>50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF;1206≥10μF</td> </tr> <tr> <td>35V: 0603≥1μF;</td> <td rowspan="5">RxC≥50Ω·F.</td> </tr> <tr> <td>25V:0201≥0.1μF;0402≥0.22μF;0603≥10μF;0805≥10μF;1206≥22μF</td> </tr> <tr> <td>16V:0201≥0.22μF;0402≥1μF 0603≥10μF</td> </tr> <tr> <td>10V: 0201≥0.1μF;0402≥1μF; 0603≥10μF; 0805≥47μF</td> </tr> <tr> <td>6.3V: 0201≥0.1μF; 0603≥4.7μF; 0805≥47μF;1206≥10μF</td> </tr> <tr> <td>4V:0603≥22μF; 0805≥47μF; 1206≥100μF</td> <td></td> </tr> </tbody> </table>	Rated voltage	IR	100V: X7R	10GΩ or RxC≥100Ω·F whichever is smaller	50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF	35V:0805≥2.2μF;1206≥2.2μF;1210≥10μF	25V:0402≥1μF;0603≥2.2μF;0805≥2.2μF;1206≥10μF;1210≥10μF	16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF	10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF;1206≥4.7μF;1210≥47μF	RxC≥50Ω·F.	6.3V ; 4V	All X6S items	100V: 1210≥3.3μF	50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF;1206≥10μF	35V: 0603≥1μF;	RxC≥50Ω·F.	25V:0201≥0.1μF;0402≥0.22μF;0603≥10μF;0805≥10μF;1206≥22μF	16V:0201≥0.22μF;0402≥1μF 0603≥10μF	10V: 0201≥0.1μF;0402≥1μF; 0603≥10μF; 0805≥47μF	6.3V: 0201≥0.1μF; 0603≥4.7μF; 0805≥47μF;1206≥10μF	4V:0603≥22μF; 0805≥47μF; 1206≥100μF																															
Rated voltage	IR																																																						
100V: X7R	10GΩ or RxC≥100Ω·F whichever is smaller																																																						
50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF																																																							
35V:0805≥2.2μF;1206≥2.2μF;1210≥10μF																																																							
25V:0402≥1μF;0603≥2.2μF;0805≥2.2μF;1206≥10μF;1210≥10μF																																																							
16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF																																																							
10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF;1206≥4.7μF;1210≥47μF	RxC≥50Ω·F.																																																						
6.3V ; 4V																																																							
All X6S items																																																							
100V: 1210≥3.3μF																																																							
50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF;1206≥10μF																																																							
35V: 0603≥1μF;	RxC≥50Ω·F.																																																						
25V:0201≥0.1μF;0402≥0.22μF;0603≥10μF;0805≥10μF;1206≥22μF																																																							
16V:0201≥0.22μF;0402≥1μF 0603≥10μF																																																							
10V: 0201≥0.1μF;0402≥1μF; 0603≥10μF; 0805≥47μF																																																							
6.3V: 0201≥0.1μF; 0603≥4.7μF; 0805≥47μF;1206≥10μF																																																							
4V:0603≥22μF; 0805≥47μF; 1206≥100μF																																																							
6	Temperature Coefficient	With no electrical load. <table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> </tr> </thead> <tbody> <tr> <td>NP0</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X5R</td> <td>-55~ 85°C at 25°C</td> </tr> <tr> <td>X6S</td> <td>-55~105°C at 25°C</td> </tr> <tr> <td>Y5V</td> <td>-25~ 85°C at 20°C</td> </tr> </tbody> </table> *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement voltage for Class II: <table border="1"> <thead> <tr> <th>01005</th> <th>0201</th> </tr> </thead> <tbody> <tr> <td>Cap≤0.01μF: 0.5V</td> <td>Cap<0.1μF:1V</td> </tr> <tr> <td>Cap>0.01μF: 0.2V</td> <td>0.1μF≤Cap<1μF: 0.2V</td> </tr> <tr> <td></td> <td>Cap≥1μF: 0.1V</td> </tr> <tr> <td></td> <td>*0201X104/16V: 0.5V</td> </tr> <tr> <th>0402</th> <th>0603</th> </tr> <tr> <td>Cap<1μF: 1V</td> <td>Cap<1μF: 1V</td> </tr> <tr> <td>Cap=1μF: 0.5V</td> <td>1μF≤Cap≤4.7μF: 0.5V</td> </tr> <tr> <td>1μF<Cap<10μF: 0.2V</td> <td>Cap>4.7μF: 0.2V</td> </tr> <tr> <td>Cap≥10μF: 0.1V</td> <td></td> </tr> <tr> <th>0805</th> <th>1206/1210</th> </tr> <tr> <td>Cap<10μF: 1V</td> <td>Cap≤10μF: 1V</td> </tr> <tr> <td>Cap=10μF: 0.5V</td> <td>10μF<Cap≤100μF: 0.5V</td> </tr> <tr> <td>Cap>10μF: 0.2V</td> <td>Cap>100μF: 0.2V</td> </tr> </tbody> </table>	T.C.	Operating Temp	NP0	-55~125°C at 25°C	X7R	-55~125°C at 25°C	X5R	-55~ 85°C at 25°C	X6S	-55~105°C at 25°C	Y5V	-25~ 85°C at 20°C	01005	0201	Cap≤0.01μF: 0.5V	Cap<0.1μF:1V	Cap>0.01μF: 0.2V	0.1μF≤Cap<1μF: 0.2V		Cap≥1μF: 0.1V		*0201X104/16V: 0.5V	0402	0603	Cap<1μF: 1V	Cap<1μF: 1V	Cap=1μF: 0.5V	1μF≤Cap≤4.7μF: 0.5V	1μF<Cap<10μF: 0.2V	Cap>4.7μF: 0.2V	Cap≥10μF: 0.1V		0805	1206/1210	Cap<10μF: 1V	Cap≤10μF: 1V	Cap=10μF: 0.5V	10μF<Cap≤100μF: 0.5V	Cap>10μF: 0.2V	Cap>100μF: 0.2V	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> </tr> </thead> <tbody> <tr> <td>NP0</td> <td>Within ±30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within ±15%</td> </tr> <tr> <td>X5R</td> <td>Within ±15%</td> </tr> <tr> <td>X6S</td> <td>Within ±22%</td> </tr> <tr> <td>Y5V</td> <td>Within +30%/-80%</td> </tr> </tbody> </table>	T.C.	Operating Temp	NP0	Within ±30ppm/°C	X7R	Within ±15%	X5R	Within ±15%	X6S	Within ±22%	Y5V	Within +30%/-80%
T.C.	Operating Temp																																																						
NP0	-55~125°C at 25°C																																																						
X7R	-55~125°C at 25°C																																																						
X5R	-55~ 85°C at 25°C																																																						
X6S	-55~105°C at 25°C																																																						
Y5V	-25~ 85°C at 20°C																																																						
01005	0201																																																						
Cap≤0.01μF: 0.5V	Cap<0.1μF:1V																																																						
Cap>0.01μF: 0.2V	0.1μF≤Cap<1μF: 0.2V																																																						
	Cap≥1μF: 0.1V																																																						
	*0201X104/16V: 0.5V																																																						
0402	0603																																																						
Cap<1μF: 1V	Cap<1μF: 1V																																																						
Cap=1μF: 0.5V	1μF≤Cap≤4.7μF: 0.5V																																																						
1μF<Cap<10μF: 0.2V	Cap>4.7μF: 0.2V																																																						
Cap≥10μF: 0.1V																																																							
0805	1206/1210																																																						
Cap<10μF: 1V	Cap≤10μF: 1V																																																						
Cap=10μF: 0.5V	10μF<Cap≤100μF: 0.5V																																																						
Cap>10μF: 0.2V	Cap>100μF: 0.2V																																																						
T.C.	Operating Temp																																																						
NP0	Within ±30ppm/°C																																																						
X7R	Within ±15%																																																						
X5R	Within ±15%																																																						
X6S	Within ±22%																																																						
Y5V	Within +30%/-80%																																																						

Aillen® Multilayer Ceramic Capacitors

No.	Item	Test Condition	Requirements															
7	Adhesive Strength of Termination	<ul style="list-style-type: none"> * Pressurizing force: 1N (0201) and 5N (≤ 0603) and 10N (>0603) * Test time: 10\pm1 sec. 	<ul style="list-style-type: none"> * No remarkable damage or removal of the terminations. 															
8	Vibration Resistance	<ul style="list-style-type: none"> * Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) <p>To apply de-aging at 150°C for 1hr then set for 24\pm2 hrs at room temp.</p> <p>Cap./DF(Q) Measurement to be made after de-aging a 150°C for 1hr then set for 24\pm2 hrs at room temp.</p>	<ul style="list-style-type: none"> * No remarkable damage or removal of the terminations. * No remarkable damage. * Cap change and Q/D.F.: To meet initial spec. 															
9	Solder ability	<ul style="list-style-type: none"> * Solder temperature: 235\pm5°C * Dipping time: 2\pm0.5 sec. 	95% min. coverage of all metalized area.															
10	Bending Test	<ul style="list-style-type: none"> * The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5\pm1 sec. * Measurement to be made after keeping at room temp. for 24\pm2 hrs. 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within \pm5% or 0.5pF whichever is larger X7R, X5R, X6S: within \pm12.5% Y5V: within \pm30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.) 															
11	Resistance to Soldering Heat	<ul style="list-style-type: none"> * Solder temperature: 260\pm5°C * Dipping time: 10\pm1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150\pm0/-10°C for 1 hr and then set for 24\pm2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24\pm2 hrs. 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within \pm2.5% or 0.25pF whichever is larger X7R, X5R, X6S: within \pm7.5% Y5V: within \pm20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge. 															
12	Temperature Cycle	<p>* Conduct the five cycles according to the temperatures and time.</p> <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp.+0/-3</td> <td>30\pm3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp.+3/-0</td> <td>30\pm3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * Before initial measurement (Class II only): Perform 150\pm0/-10°C for 1 hr and then set for 24\pm2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24\pm2 hrs. 	Step	Temp. (°C)	Time (min.)	1	Min. operating temp.+0/-3	30 \pm 3	2	Room temp.	2~3	3	Max. operating temp.+3/-0	30 \pm 3	4	Room temp.	2~3	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within \pm2.5% or 0.25pF whichever is larger X7R, X5R, X6S: within \pm7.5% Y5V: within \pm20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements.
Step	Temp. (°C)	Time (min.)																
1	Min. operating temp.+0/-3	30 \pm 3																
2	Room temp.	2~3																
3	Max. operating temp.+3/-0	30 \pm 3																
4	Room temp.	2~3																

Aillen® Multilayer Ceramic Capacitors

13	Humidity (Damp Heat)Steady State	<p>* Test temp.: 40±2°C * Humidity: 90~95% RH * Test time: 500+24/-0hrs. *Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.</p>	<p>* No remarkable damage. * Cap change: NP0: within ±5% or 0.5pF whichever is larger X7R, X5R, X6S: ≥10V**, within ±12.5%; 6.3V within ±25%;≤ TT series & C ≥ 1uF, within ±25% **10V: 0603 ≥ 4.7μF; 0402 ≥ 1μF; 0201 ≥ 0.1μF, within ±25%; Y5V: ≥10V, within ±30%; 6.3V, within +30/≤ -40% * Q/D.F. value: NP0: More than 30pF Q ≥ 350, 10pF ≤ C ≤ 30pF, Q ≥ 275+2.5C Less than 10pF Q ≥ 200+10C X7R, X5R, X6S:</p> <table border="1" data-bbox="774 582 1460 1153"> <thead> <tr> <th>Rated vol.</th> <th>D.F. ≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="3">≥100V</td> <td rowspan="3">≤3%</td> <td>≤ 6%</td> <td>1206 ≥ 0.47μF</td> </tr> <tr> <td>≤ 7.5%</td> <td>0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF; 1210 ≥ 2.2μF</td> </tr> <tr> <td>≤ 20%</td> <td>0805 > 0.22μF; 1210 ≥ 3.3μF</td> </tr> <tr> <td rowspan="3">50V</td> <td rowspan="3">≤3%</td> <td>≤ 6%</td> <td>0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF</td> </tr> <tr> <td>≤ 10%</td> <td>0201 ≥ 0.01μF; 1210 ≥ 4.7μF</td> </tr> <tr> <td>≤ 20%</td> <td>0402 ≥ 0.012μF; 0603 > 0.1μF 0805 ≥ 1μF(0805/X7R > 0.47μF); 1206 ≥ 2.2μF; 1210 ≥ 10μF</td> </tr> <tr> <td>35V</td> <td>≤5%</td> <td>≤20%</td> <td>0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">≤5%</td> <td>≤10%</td> <td>0201 ≥ 0.01μF; 0805 ≥ 1 μF; 1210 ≥ 10μF</td> </tr> <tr> <td>≤14%</td> <td>0603 ≥ 0.33μF;</td> </tr> <tr> <td>≤15%</td> <td>0201 ≥ 0.1μF; 0402 ≥ 0.10μF & (0402/X7R ≥ 0.056μF); 0603 ≥ 0.47μF;</td> </tr> <tr> <td>≤20%</td> <td>0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF(1210/X5R ≥ 10μF)</td> </tr> <tr> <td rowspan="2">16V</td> <td rowspan="2">≤5%</td> <td>≤10%</td> <td>0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0201 ≥ 0.01μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.033μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF</td> </tr> <tr> <td rowspan="2">10V</td> <td rowspan="2">≤7.5%</td> <td>≤15%</td> <td>0201 ≥ 0.012μF; 0402 ≥ 0.22μF;</td> </tr> <tr> <td>≤20%</td> <td>0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF</td> </tr> <tr> <td rowspan="2">6.3V</td> <td rowspan="2">≤15%</td> <td>≤30%</td> <td>0201 ≥ 0.1μF; 0402 ≥ 1μF(0402/X6S ≥ 0.47μF); 0603 ≥ 10μF;</td> </tr> <tr> <td>---</td> <td>0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μ</td> </tr> <tr> <td>4V</td> <td>≤20%</td> <td>---</td> <td>---</td> </tr> </tbody> </table> <p>Y5V</p> <table border="1" data-bbox="774 1198 1460 1556"> <thead> <tr> <th>Rated vol.</th> <th>D.F. ≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="2">≥50V</td> <td rowspan="2">≤7.5%</td> <td>≤10%</td> <td>0603 ≥ 0.1 μF; 0805 ≥ 0.47μF; 1210 ≥ 4.7μF</td> </tr> <tr> <td>≤20%</td> <td>1210 ≥ 6.8μF</td> </tr> <tr> <td>35V</td> <td>≤10%</td> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">≤7.5%</td> <td>≤10%</td> <td>0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF</td> </tr> <tr> <td>≤12.5%</td> <td>0402 ≥ 0.068μF; 0603 ≥ 0.68μF</td> </tr> <tr> <td>16V (C < 1.0μF)</td> <td>≤10%</td> <td>≤20%</td> <td>0402 ≥ 0.22μF</td> </tr> <tr> <td>16V (C ≥ 1.0μF)</td> <td>≤12.5%</td> <td>≤20%</td> <td>0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF</td> </tr> <tr> <td>10V</td> <td>≤20%</td> <td>≤30%</td> <td>0402 ≥ 0.47μF</td> </tr> <tr> <td>6.3V</td> <td>≤30%</td> <td>---</td> <td>---</td> </tr> </tbody> </table> <p>*I.R.: ≥10V, 1GΩ or 50 Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)</p> <table border="1" data-bbox="774 1657 1460 1926"> <thead> <tr> <th>Rated voltage</th> <th>I.R.</th> </tr> </thead> <tbody> <tr> <td>100V: X7R; 1210 ≥ 3.3μF</td> <td rowspan="7">1GΩ or RxC ≥ 10Ω-F whichever is smaller</td> </tr> <tr> <td>50V: 0402 > 0.01μF; 0603 ≥ 1μF; 0805 ≥ 1μF; 1206 ≥ 4.7μF; 1210 ≥ 4.7μF</td> </tr> <tr> <td>35V: 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1210 ≥ 10μF;</td> </tr> <tr> <td>25V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 2.2μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 10μF</td> </tr> <tr> <td>16V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 47μF</td> </tr> <tr> <td>10V: 0201 ≥ 47nF; 0402 ≥ 0.47μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 47μF</td> </tr> <tr> <td>6.3V; 4V; All X6S items</td> </tr> </tbody> </table>	Rated vol.	D.F. ≤	Exception of D.F. ≤		≥100V	≤3%	≤ 6%	1206 ≥ 0.47μF	≤ 7.5%	0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF; 1210 ≥ 2.2μF	≤ 20%	0805 > 0.22μF; 1210 ≥ 3.3μF	50V	≤3%	≤ 6%	0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF	≤ 10%	0201 ≥ 0.01μF; 1210 ≥ 4.7μF	≤ 20%	0402 ≥ 0.012μF; 0603 > 0.1μF 0805 ≥ 1μF(0805/X7R > 0.47μF); 1206 ≥ 2.2μF; 1210 ≥ 10μF	35V	≤5%	≤20%	0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF	25V	≤5%	≤10%	0201 ≥ 0.01μF; 0805 ≥ 1 μF; 1210 ≥ 10μF	≤14%	0603 ≥ 0.33μF;	≤15%	0201 ≥ 0.1μF; 0402 ≥ 0.10μF & (0402/X7R ≥ 0.056μF); 0603 ≥ 0.47μF;	≤20%	0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF(1210/X5R ≥ 10μF)	16V	≤5%	≤10%	0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF	≤15%	0201 ≥ 0.01μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.033μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF	10V	≤7.5%	≤15%	0201 ≥ 0.012μF; 0402 ≥ 0.22μF;	≤20%	0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF	6.3V	≤15%	≤30%	0201 ≥ 0.1μF; 0402 ≥ 1μF(0402/X6S ≥ 0.47μF); 0603 ≥ 10μF;	---	0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μ	4V	≤20%	---	---	Rated vol.	D.F. ≤	Exception of D.F. ≤		≥50V	≤7.5%	≤10%	0603 ≥ 0.1 μF; 0805 ≥ 0.47μF; 1210 ≥ 4.7μF	≤20%	1210 ≥ 6.8μF	35V	≤10%	---	---	25V	≤7.5%	≤10%	0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF	≤15%	0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF	≤12.5%	0402 ≥ 0.068μF; 0603 ≥ 0.68μF	16V (C < 1.0μF)	≤10%	≤20%	0402 ≥ 0.22μF	16V (C ≥ 1.0μF)	≤12.5%	≤20%	0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF	10V	≤20%	≤30%	0402 ≥ 0.47μF	6.3V	≤30%	---	---	Rated voltage	I.R.	100V: X7R; 1210 ≥ 3.3μF	1GΩ or RxC ≥ 10Ω-F whichever is smaller	50V: 0402 > 0.01μF; 0603 ≥ 1μF; 0805 ≥ 1μF; 1206 ≥ 4.7μF; 1210 ≥ 4.7μF	35V: 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1210 ≥ 10μF;	25V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 2.2μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 10μF	16V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 47μF	10V: 0201 ≥ 47nF; 0402 ≥ 0.47μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 47μF	6.3V; 4V; All X6S items
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																																																																									
≥100V	≤3%	≤ 6%	1206 ≥ 0.47μF																																																																																																								
		≤ 7.5%	0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF; 1210 ≥ 2.2μF																																																																																																								
		≤ 20%	0805 > 0.22μF; 1210 ≥ 3.3μF																																																																																																								
50V	≤3%	≤ 6%	0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF																																																																																																								
		≤ 10%	0201 ≥ 0.01μF; 1210 ≥ 4.7μF																																																																																																								
		≤ 20%	0402 ≥ 0.012μF; 0603 > 0.1μF 0805 ≥ 1μF(0805/X7R > 0.47μF); 1206 ≥ 2.2μF; 1210 ≥ 10μF																																																																																																								
35V	≤5%	≤20%	0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF																																																																																																								
25V	≤5%	≤10%	0201 ≥ 0.01μF; 0805 ≥ 1 μF; 1210 ≥ 10μF																																																																																																								
		≤14%	0603 ≥ 0.33μF;																																																																																																								
		≤15%	0201 ≥ 0.1μF; 0402 ≥ 0.10μF & (0402/X7R ≥ 0.056μF); 0603 ≥ 0.47μF;																																																																																																								
		≤20%	0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF(1210/X5R ≥ 10μF)																																																																																																								
16V	≤5%	≤10%	0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF																																																																																																								
		≤15%	0201 ≥ 0.01μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.033μF; 0603 > 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF																																																																																																								
10V	≤7.5%	≤15%	0201 ≥ 0.012μF; 0402 ≥ 0.22μF;																																																																																																								
		≤20%	0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF																																																																																																								
6.3V	≤15%	≤30%	0201 ≥ 0.1μF; 0402 ≥ 1μF(0402/X6S ≥ 0.47μF); 0603 ≥ 10μF;																																																																																																								
		---	0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μ																																																																																																								
4V	≤20%	---	---																																																																																																								
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																																																																									
≥50V	≤7.5%	≤10%	0603 ≥ 0.1 μF; 0805 ≥ 0.47μF; 1210 ≥ 4.7μF																																																																																																								
		≤20%	1210 ≥ 6.8μF																																																																																																								
35V	≤10%	---	---																																																																																																								
25V	≤7.5%	≤10%	0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF																																																																																																								
		≤15%	0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF																																																																																																								
		≤12.5%	0402 ≥ 0.068μF; 0603 ≥ 0.68μF																																																																																																								
16V (C < 1.0μF)	≤10%	≤20%	0402 ≥ 0.22μF																																																																																																								
16V (C ≥ 1.0μF)	≤12.5%	≤20%	0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF																																																																																																								
10V	≤20%	≤30%	0402 ≥ 0.47μF																																																																																																								
6.3V	≤30%	---	---																																																																																																								
Rated voltage	I.R.																																																																																																										
100V: X7R; 1210 ≥ 3.3μF	1GΩ or RxC ≥ 10Ω-F whichever is smaller																																																																																																										
50V: 0402 > 0.01μF; 0603 ≥ 1μF; 0805 ≥ 1μF; 1206 ≥ 4.7μF; 1210 ≥ 4.7μF																																																																																																											
35V: 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1210 ≥ 10μF;																																																																																																											
25V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 2.2μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 10μF																																																																																																											
16V: 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 10μF; 1210 ≥ 47μF																																																																																																											
10V: 0201 ≥ 47nF; 0402 ≥ 0.47μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 47μF																																																																																																											
6.3V; 4V; All X6S items																																																																																																											

Aillen® Multilayer Ceramic Capacitors

14	Humidity (Damp Heat) Load	<p>* Test temp.: 40±2°C * Humidity: 90~95%RH * Test time: 500+24/-0 hrs. * To apply voltage: rated voltage. * Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.* Cap./DF(Q)/I.R. Measurement to be made after de-aging at 150° C for 1hr.then set for 24±2 hrs at room temp</p>	<p>* No remarkable damage. Cap change: NP0: ±7.5% or 0.75pF whichever is larger. X7R, X5R, X6S: ≥10V**, within ±12.5%; ≤ 6.3V within ±25%; TT series & C ≥ 1uF, within ±25% **10V: 0603 4.7≥ μF;0402 ≥1 μF;0201≥ 0.1 μF, within ±25%; Y5V: ≥10V, within ±30%; ≤ 6.3V, within +30/-40% Q/D.F. value: NP0: C≥30pF,Q≥200;C<30pF, Q≥100+10/3C X7R, X5R, X6S:</p>																																																						
			<table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td>≥100V</td> <td>≤3%</td> <td>≤6%</td> <td>1206≥0.47μF</td> </tr> <tr> <td></td> <td></td> <td>≤7.5%</td> <td>0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF;1210 ≥ 2.2μF</td> </tr> <tr> <td rowspan="3">50V</td> <td rowspan="3">≤3%</td> <td>≤6%</td> <td>0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF</td> </tr> <tr> <td>≤10%</td> <td>1210≥4.7μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF</td> </tr> <tr> <td>35V</td> <td>≤5%</td> <td>≤20%</td> <td>0603≥1 μF;0805≥2.2μF; 1210≥10 μF</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">≤5%</td> <td>≤10%</td> <td>0201≥0.01μF;0805≥1 μF; 1210≥10μF</td> </tr> <tr> <td>≤14%</td> <td>0603≥0.33μF; 1206≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥1μF</td> </tr> <tr> <td rowspan="2">16V</td> <td rowspan="2">≤5%</td> <td>≤10%</td> <td>0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td rowspan="2">10V</td> <td rowspan="2">≤7.5%</td> <td>≤15%</td> <td>0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF</td> </tr> <tr> <td>≤20%</td> <td>0201≥0.1μF; 0402≥1 μF</td> </tr> <tr> <td>6.3V</td> <td>≤15%</td> <td>≤30%</td> <td>0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;</td> </tr> <tr> <td>4V</td> <td>≤20%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F. ≤		≥100V	≤3%	≤6%	1206≥0.47μF			≤7.5%	0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF;1210 ≥ 2.2μF	50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF	≤10%	1210≥4.7μF	≤20%	0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF	35V	≤5%	≤20%	0603≥1 μF;0805≥2.2μF; 1210≥10 μF	25V	≤5%	≤10%	0201≥0.01μF;0805≥1 μF; 1210≥10μF	≤14%	0603≥0.33μF; 1206≥4.7μF	≤15%	0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF	≤20%	0402≥1μF	16V	≤5%	≤10%	0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF	≤15%	0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF	10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF	≤20%	0201≥0.1μF; 0402≥1 μF	6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;	4V	≤20%	---	---
			Rated vol.	D.F.≤	Exception of D.F. ≤																																																				
			≥100V	≤3%	≤6%	1206≥0.47μF																																																			
					≤7.5%	0603 ≥ 0.068μF, 0805 > 0.1μF, 1206 ≥ 1μF;1210 ≥ 2.2μF																																																			
			50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF																																																			
					≤10%	1210≥4.7μF																																																			
					≤20%	0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF																																																			
			35V	≤5%	≤20%	0603≥1 μF;0805≥2.2μF; 1210≥10 μF																																																			
			25V	≤5%	≤10%	0201≥0.01μF;0805≥1 μF; 1210≥10μF																																																			
					≤14%	0603≥0.33μF; 1206≥4.7μF																																																			
					≤15%	0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF																																																			
					≤20%	0402≥1μF																																																			
			16V	≤5%	≤10%	0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF																																																			
≤15%	0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF																																																								
10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF																																																						
		≤20%	0201≥0.1μF; 0402≥1 μF																																																						
6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;																																																						
4V	≤20%	---	---																																																						
<p>Y5V</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td>≥50V</td> <td>≤7.5%</td> <td>≤10%</td> <td>0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF</td> </tr> <tr> <td></td> <td></td> <td>≤20%</td> <td>1210 ≥ 6.8μF</td> </tr> <tr> <td>35V</td> <td>≤10%</td> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">≤7.5%</td> <td>≤10%</td> <td>0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>≤12.5%</td> <td>0402≥0.068μF;0603≥0.68μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>≤10%</td> <td>≤20%</td> <td>0402≥0.22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>≤12.5%</td> <td>≤20%</td> <td>0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>10V</td> <td>≤20%</td> <td>≤30%</td> <td>0402≥0.47μF</td> </tr> <tr> <td>6.3V</td> <td>≤30%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F. ≤		≥50V	≤7.5%	≤10%	0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF			≤20%	1210 ≥ 6.8μF	35V	≤10%	---	---	25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF	≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF	≤12.5%	0402≥0.068μF;0603≥0.68μF	16V (C<1.0μF)	≤10%	≤20%	0402≥0.22μF	16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF	10V	≤20%	≤30%	0402≥0.47μF	6.3V	≤30%	---	---																	
Rated vol.	D.F.≤	Exception of D.F. ≤																																																							
≥50V	≤7.5%	≤10%	0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF																																																						
		≤20%	1210 ≥ 6.8μF																																																						
35V	≤10%	---	---																																																						
25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF																																																						
		≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF																																																						
		≤12.5%	0402≥0.068μF;0603≥0.68μF																																																						
16V (C<1.0μF)	≤10%	≤20%	0402≥0.22μF																																																						
16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF																																																						
10V	≤20%	≤30%	0402≥0.47μF																																																						
6.3V	≤30%	---	---																																																						
<p>*I.R.: ≥10V, 500MΩ or 25 Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)</p> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>I.R.</th> </tr> </thead> <tbody> <tr> <td>100V: X7R;1210≥3.3μF</td> <td rowspan="7" style="text-align: center; vertical-align: middle;">1GΩ or Rx≥10Ω-F whichever is smaller</td> </tr> <tr> <td>50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF</td> </tr> <tr> <td>35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;</td> </tr> <tr> <td>25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF</td> </tr> <tr> <td>16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF</td> </tr> <tr> <td>10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF</td> </tr> <tr> <td>6.3V; 4V; All X6S items</td> </tr> </tbody> </table>	Rated voltage	I.R.	100V: X7R;1210≥3.3μF	1GΩ or Rx≥10Ω-F whichever is smaller	50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF	35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;	25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF	16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF	10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF	6.3V; 4V; All X6S items																																															
Rated voltage	I.R.																																																								
100V: X7R;1210≥3.3μF	1GΩ or Rx≥10Ω-F whichever is smaller																																																								
50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF																																																									
35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;																																																									
25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF																																																									
16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF																																																									
10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF																																																									
6.3V; 4V; All X6S items																																																									



Aillen® Multilayer Ceramic Capacitors

15	High Temperature Load (Endurance)	<p>*Test temp.: NP0, X7R: 125±3°C X6S: 105±3°C X5R, Y5V: 85±3°C *Test time: 1000+24/-0 hrs. *To apply voltage: (1) ≤ 6.3V or C 10≥ μF : 150% of rated voltage. (2) 10V≤ Ur<500V: 200% of rated voltage. (3) 500V: 150% of rated voltage. (4) Ur≥ 630V: 120% of rated voltage. (5) 100% of rated voltage for below range</p>	<p>* No remarkable damage. Cap change: NP0: ±3.0% or ±0.3pF whichever is larger X7R, X5R, X6S: ≥10V**, within ±12.5%; ≤6.3V within ±25%; **10V: 0603≥4.7μF;0402≥ 1μF;0201≥0.1μF, within ±25%; Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40% Q/D.F. value: NP0: More than 30pF, Q≥350 10pF≤C<30pF, Q≥275+2.5C Less than 10pF, Q≥200+10C X7R, X5R, X7R, X5R,X6S:</p>																																																																																																														
		<table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td rowspan="2">0201</td> <td rowspan="2">X5R/X7R/X6S</td> <td>≤10V</td> <td>C≥0.1μF</td> </tr> <tr> <td>≥16V</td> <td>C>0.1μF</td> </tr> <tr> <td rowspan="4">0402</td> <td rowspan="2">X5R</td> <td>≤16V</td> <td>C>1.0μF</td> </tr> <tr> <td>25V,50V</td> <td>C≥1.0μF</td> </tr> <tr> <td rowspan="2">X6S</td> <td>6.3V,10V</td> <td>C>1.0μF</td> </tr> <tr> <td>16V,25V</td> <td>C≥1.0μF</td> </tr> <tr> <td>X7R/Y5V</td> <td>6.3V,10V</td> <td>C≥1.0μF</td> </tr> <tr> <td rowspan="3">0603</td> <td rowspan="2">X5R/ X7R/ X6S</td> <td>4V</td> <td>C≥22μF</td> </tr> <tr> <td>6.3V,10V</td> <td>C≥4.7μF</td> </tr> <tr> <td>X5R/ X6S</td> <td>25V</td> <td>C≥1.0μF</td> </tr> <tr> <td rowspan="4">0805</td> <td rowspan="2">X5R/X7R/X6S</td> <td>4V</td> <td>C>47μF</td> </tr> <tr> <td>6.3V</td> <td>C≥22μF</td> </tr> <tr> <td rowspan="2">X6S/X7R</td> <td>10V,50V</td> <td>C≥10μF</td> </tr> <tr> <td>16V,25V</td> <td>C≥10μF</td> </tr> <tr> <td>X5R</td> <td></td> <td>C≥22μF</td> </tr> <tr> <td>1206</td> <td>X5R/X7R/ X6S</td> <td>≤6.3V</td> <td>C≥47μF</td> </tr> <tr> <td rowspan="2">1210</td> <td rowspan="2">X5R/X7R/ X6S</td> <td>16V</td> <td>C≥47μF</td> </tr> <tr> <td>X7R</td> <td>100V</td> <td>C≥3.3μF</td> </tr> </tbody> </table>	Size	Dielectric	Rated voltage	Capacitance	0201	X5R/X7R/X6S	≤10V	C≥0.1μF	≥16V	C>0.1μF	0402	X5R	≤16V	C>1.0μF	25V,50V	C≥1.0μF	X6S	6.3V,10V	C>1.0μF	16V,25V	C≥1.0μF	X7R/Y5V	6.3V,10V	C≥1.0μF	0603	X5R/ X7R/ X6S	4V	C≥22μF	6.3V,10V	C≥4.7μF	X5R/ X6S	25V	C≥1.0μF	0805	X5R/X7R/X6S	4V	C>47μF	6.3V	C≥22μF	X6S/X7R	10V,50V	C≥10μF	16V,25V	C≥10μF	X5R		C≥22μF	1206	X5R/X7R/ X6S	≤6.3V	C≥47μF	1210	X5R/X7R/ X6S	16V	C≥47μF	X7R	100V	C≥3.3μF	<table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="2">≥100V</td> <td rowspan="2">≤3%</td> <td>≤6%</td> <td>1206≥0.47μF</td> </tr> <tr> <td>≤7.5%</td> <td>0805>0.1μF, 0603≥0.068 μF, 1206>1 μF</td> </tr> <tr> <td rowspan="3">50V</td> <td rowspan="3">≤3%</td> <td>≤6%</td> <td>0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF</td> </tr> <tr> <td>≤10%</td> <td>1210≥ 4.7μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF</td> </tr> <tr> <td>35V</td> <td>≤5%</td> <td>≤20%</td> <td>0603≥1 μF;0805≥2.2μF; 1210≥10 μF</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">≤5%</td> <td>≤10%</td> <td>0201≥0.01μF;0805≥1 μF; 1210≥10μF</td> </tr> <tr> <td>≤14%</td> <td>0603≥0.33μF; 1206≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥1μF</td> </tr> <tr> <td rowspan="2">16V</td> <td rowspan="2">≤5%</td> <td>≤10%</td> <td>0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>10V</td> <td>≤7.5%</td> <td>≤15%</td> <td>0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF) ;0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF</td> </tr> <tr> <td rowspan="2">6.3V</td> <td rowspan="2">≤15%</td> <td>≤30%</td> <td>0201≥0.1μF;0402≥1 μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;</td> </tr> <tr> <td>---</td> <td>---</td> </tr> <tr> <td>4V</td> <td>≤20%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F. ≤		≥100V	≤3%	≤6%	1206≥0.47μF	≤7.5%	0805>0.1μF, 0603≥0.068 μF, 1206>1 μF	50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF	≤10%	1210≥ 4.7μF	≤20%	0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF	35V	≤5%	≤20%	0603≥1 μF;0805≥2.2μF; 1210≥10 μF	25V	≤5%	≤10%	0201≥0.01μF;0805≥1 μF; 1210≥10μF	≤14%	0603≥0.33μF; 1206≥4.7μF	≤15%	0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF	≤20%	0402≥1μF	16V	≤5%	≤10%	0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF	≤15%	0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF	10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF) ;0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF	6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1 μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;	---	---	4V	≤20%	---	---
		Size	Dielectric	Rated voltage	Capacitance																																																																																																												
		0201	X5R/X7R/X6S	≤10V	C≥0.1μF																																																																																																												
				≥16V	C>0.1μF																																																																																																												
		0402	X5R	≤16V	C>1.0μF																																																																																																												
				25V,50V	C≥1.0μF																																																																																																												
			X6S	6.3V,10V	C>1.0μF																																																																																																												
				16V,25V	C≥1.0μF																																																																																																												
		X7R/Y5V	6.3V,10V	C≥1.0μF																																																																																																													
		0603	X5R/ X7R/ X6S	4V	C≥22μF																																																																																																												
				6.3V,10V	C≥4.7μF																																																																																																												
			X5R/ X6S	25V	C≥1.0μF																																																																																																												
		0805	X5R/X7R/X6S	4V	C>47μF																																																																																																												
				6.3V	C≥22μF																																																																																																												
X6S/X7R	10V,50V		C≥10μF																																																																																																														
	16V,25V		C≥10μF																																																																																																														
X5R		C≥22μF																																																																																																															
1206	X5R/X7R/ X6S	≤6.3V	C≥47μF																																																																																																														
1210	X5R/X7R/ X6S	16V	C≥47μF																																																																																																														
		X7R	100V	C≥3.3μF																																																																																																													
Rated vol.	D.F.≤	Exception of D.F. ≤																																																																																																															
≥100V	≤3%	≤6%	1206≥0.47μF																																																																																																														
		≤7.5%	0805>0.1μF, 0603≥0.068 μF, 1206>1 μF																																																																																																														
50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF; 1206≥0.47μF																																																																																																														
		≤10%	1210≥ 4.7μF																																																																																																														
		≤20%	0402≥0.1μF;0603>0.1μF;0805≥1μF; 1206≥2.2μF;1210≥10μF																																																																																																														
35V	≤5%	≤20%	0603≥1 μF;0805≥2.2μF; 1210≥10 μF																																																																																																														
25V	≤5%	≤10%	0201≥0.01μF;0805≥1 μF; 1210≥10μF																																																																																																														
		≤14%	0603≥0.33μF; 1206≥4.7μF																																																																																																														
		≤15%	0402≥0.10μF;0603≥0.47μF; 0805≥2.2μF;1206≥6.8μF ; 1210≥22μF																																																																																																														
		≤20%	0402≥1μF																																																																																																														
16V	≤5%	≤10%	0201≥0.01μF;0402≥0.033μF;0603≥0.15μF;0805 ≥0.68μF;1206≥2.2μF;1210≥4.7μF																																																																																																														
		≤15%	0201≥0.1μF;0402≥0.22μF;0603≥0.68μF;0805≥2.2μF; 1206≥4.7μF; 1210≥22μF																																																																																																														
10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF) ;0603≥0.33μF;0805≥2.2μF;1206≥2.2μF;1210≥22 μF																																																																																																														
6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1 μF;0603≥10μF;0805≥4.7μF; 1206≥47μF ;1210≥ 100μF;																																																																																																														
		---	---																																																																																																														
4V	≤20%	---	---																																																																																																														
(6) 150% of rated voltage for below range.	<table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td rowspan="2">0201</td> <td rowspan="2">X5R/ X6S</td> <td>16V,25V</td> <td>C=0.1μF</td> </tr> <tr> <td>X7R</td> <td>16V</td> <td>C≥0.022μF</td> </tr> <tr> <td rowspan="2">0402</td> <td rowspan="2">X5R/X7R/X6S</td> <td>50V</td> <td>C>0.01μF</td> </tr> <tr> <td>10-25V</td> <td>C≥0.22μF</td> </tr> <tr> <td rowspan="4">0603</td> <td rowspan="2">Y5V</td> <td>16V</td> <td>C≥0.47μF</td> </tr> <tr> <td>50V</td> <td>C>0.1μF</td> </tr> <tr> <td rowspan="2">X7R</td> <td>25V</td> <td>C=1.0μF</td> </tr> <tr> <td>50V</td> <td>C≥1.0μF</td> </tr> <tr> <td rowspan="3">0805</td> <td rowspan="2">X5R/X7R/X6S</td> <td>10V,16V</td> <td>C≥1.0μF</td> </tr> <tr> <td>16V</td> <td>C≥2.2μF</td> </tr> <tr> <td>Y5V</td> <td>100V</td> <td>C≥0.47μF</td> </tr> <tr> <td rowspan="4">1206</td> <td rowspan="2">X5R/X7R/X6S</td> <td>50V</td> <td>C≥1.0μF</td> </tr> <tr> <td>35V</td> <td>C≥2.2μF</td> </tr> <tr> <td rowspan="2">Y5V</td> <td>10-25V</td> <td>C≥4.7μF</td> </tr> <tr> <td>16V</td> <td>C≥4.7μF</td> </tr> <tr> <td rowspan="2">1210</td> <td rowspan="2">X5R/X7R/X6S</td> <td>100V</td> <td>C>1.0μF</td> </tr> <tr> <td>50V</td> <td>C=4.7μF</td> </tr> <tr> <td>1825 2220 2225</td> <td>X7R</td> <td>100V-250V</td> <td>C≥1.0μF</td> </tr> </tbody> </table>	Size	Dielectric	Rated voltage	Capacitance	0201	X5R/ X6S	16V,25V	C=0.1μF	X7R	16V	C≥0.022μF	0402	X5R/X7R/X6S	50V	C>0.01μF	10-25V	C≥0.22μF	0603	Y5V	16V	C≥0.47μF	50V	C>0.1μF	X7R	25V	C=1.0μF	50V	C≥1.0μF	0805	X5R/X7R/X6S	10V,16V	C≥1.0μF	16V	C≥2.2μF	Y5V	100V	C≥0.47μF	1206	X5R/X7R/X6S	50V	C≥1.0μF	35V	C≥2.2μF	Y5V	10-25V	C≥4.7μF	16V	C≥4.7μF	1210	X5R/X7R/X6S	100V	C>1.0μF	50V	C=4.7μF	1825 2220 2225	X7R	100V-250V	C≥1.0μF	<p>Y5V:</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td>≥50V</td> <td>≤7.5%</td> <td>≤10%</td> <td>0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF</td> </tr> <tr> <td rowspan="2">35V</td> <td rowspan="2">≤10%</td> <td>---</td> <td>1210≅ 6.8μF</td> </tr> <tr> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">≤7.5%</td> <td>≤10%</td> <td>0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>≤12.5%</td> <td>0402≥0.068μF;0603≥0.68μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>≤10%</td> <td>≤20%</td> <td>0402≥0.22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>≤12.5%</td> <td>≤20%</td> <td>0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>10V</td> <td>≤20%</td> <td>≤30%</td> <td>0402≥0.47μF</td> </tr> <tr> <td>6.3V</td> <td>≤30%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F. ≤		≥50V	≤7.5%	≤10%	0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF	35V	≤10%	---	1210≅ 6.8μF	---	---	25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF	≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF	≤12.5%	0402≥0.068μF;0603≥0.68μF	16V (C<1.0μF)	≤10%	≤20%	0402≥0.22μF	16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF	10V	≤20%	≤30%	0402≥0.47μF	6.3V	≤30%	---	---															
Size	Dielectric	Rated voltage	Capacitance																																																																																																														
0201	X5R/ X6S	16V,25V	C=0.1μF																																																																																																														
		X7R	16V	C≥0.022μF																																																																																																													
0402	X5R/X7R/X6S	50V	C>0.01μF																																																																																																														
		10-25V	C≥0.22μF																																																																																																														
0603	Y5V	16V	C≥0.47μF																																																																																																														
		50V	C>0.1μF																																																																																																														
	X7R	25V	C=1.0μF																																																																																																														
		50V	C≥1.0μF																																																																																																														
0805	X5R/X7R/X6S	10V,16V	C≥1.0μF																																																																																																														
		16V	C≥2.2μF																																																																																																														
	Y5V	100V	C≥0.47μF																																																																																																														
1206	X5R/X7R/X6S	50V	C≥1.0μF																																																																																																														
		35V	C≥2.2μF																																																																																																														
	Y5V	10-25V	C≥4.7μF																																																																																																														
		16V	C≥4.7μF																																																																																																														
1210	X5R/X7R/X6S	100V	C>1.0μF																																																																																																														
		50V	C=4.7μF																																																																																																														
1825 2220 2225	X7R	100V-250V	C≥1.0μF																																																																																																														
Rated vol.	D.F.≤	Exception of D.F. ≤																																																																																																															
≥50V	≤7.5%	≤10%	0603≥0.1 μF;0805≥0.47μF; 1210≥4.7μF																																																																																																														
35V	≤10%	---	1210≅ 6.8μF																																																																																																														
		---	---																																																																																																														
25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF; 1206≥1μF;1210≥4.7μF																																																																																																														
		≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF; 1210≥22μF																																																																																																														
		≤12.5%	0402≥0.068μF;0603≥0.68μF																																																																																																														
16V (C<1.0μF)	≤10%	≤20%	0402≥0.22μF																																																																																																														
16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF; 1812≥47μF																																																																																																														
10V	≤20%	≤30%	0402≥0.47μF																																																																																																														
6.3V	≤30%	---	---																																																																																																														
		<p>*Before initial measurement (Class II only): To apply test voltage for 1hr at test temp. and then set for 24±2 hrs at room temp. *Measurement to be made after keeping at room temp. for 24±2 hrs.</p>	<p>*I.R.: ≥10V, 1GΩ or 50Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)</p> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>IR.</th> </tr> </thead> <tbody> <tr> <td>100V: X7R;1210≥3.3μF</td> <td rowspan="8" style="text-align: center;">1GΩ or RxC≥10Ω-F whichever is smaller</td> </tr> <tr> <td>50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF</td> </tr> <tr> <td>35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;</td> </tr> <tr> <td>25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF</td> </tr> <tr> <td>16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF</td> </tr> <tr> <td>10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF</td> </tr> <tr> <td>6.3V; 4V; All X6S items</td> </tr> <tr> <td></td> </tr> </tbody> </table>	Rated voltage	IR.	100V: X7R;1210≥3.3μF	1GΩ or RxC≥10Ω-F whichever is smaller	50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF	35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;	25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF	16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF	10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF	6.3V; 4V; All X6S items																																																																																																				
Rated voltage	IR.																																																																																																																
100V: X7R;1210≥3.3μF	1GΩ or RxC≥10Ω-F whichever is smaller																																																																																																																
50V:0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF																																																																																																																	
35V:0603≥1μF ;0805≥2.2μF;1210≥10μF;																																																																																																																	
25V:0201≥0.1μF;0402≥0.22μF;0603≥2.2μF;0805≥2.2μF; 1206≥10μF;1210≥10μF																																																																																																																	
16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF; 1206≥10μF;1210≥47μF																																																																																																																	
10V:0201≥47nF;0402≥0.47μF;0603≥0.47μF;0805≥2.2μF; 1206≥4.7μF;1210≥47μF																																																																																																																	
6.3V; 4V; All X6S items																																																																																																																	


Aillen[®] Multilayer Ceramic Capacitors

APPENDICES

▣ Tape & reel dimensions



Size	0201	0402	0603	0805			1206			1210			1808	1812	
Thickness	L	H	S,H,X	A,H	B,X	C	B	I,C,J	D,P	T	I,C,E,F	Y	C,E,F,J	C,E,F	M,U
A ₀	0.40 +/-0.10	0.70 +/-0.20	1.05 +/-0.30	1.50 +/-0.20	1.50 +/-0.20	< 1.80	1.90 +/-0.50	< 2.00	< 2.30	< 3.05	< 3.05	< 3.20	< 2.50	< 3.90	< 3.90
B ₀	0.70 +/-0.10	1.20 +/-0.20	1.80 +/-0.30	2.30 +/-0.20	2.30 +/-0.20	< 2.70	3.50 +/-0.50	< 3.70	< 4.00	< 3.80	< 3.80	< 4.00	< 5.30	< 5.30	< 5.30
T	≤ 0.55	≤ 0.80	≤ 1.20	≤ 1.15	≤ 1.20	0.23 +/-0.1	≤ 1.20	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.25 +/-0.1	0.25 +/-0.1	0.25 +/-0.1
K ₀	-	-	-	-	-	< 2.50	-	< 2.50	< 2.50	< 1.50	< 2.50	< 3.20	< 2.50	< 2.50	< 3.50
W	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	8.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30
P ₀	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10
10xP ₀	40.00 +/-0.10	40.00 +/-0.10	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20	40.00 +/-0.20
P ₁	2.00 +/-0.05	2.00 +/-0.05	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	4.00 +/-0.10	8.00 +/-0.10	8.00 +/-0.10
P ₂	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.05	2.00 +/-0.10	2.00 +/-0.10	2.00 +/-0.10
D ₀	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0
D ₁	-	-	-	-	-	1.00 +/-0.10	-	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.50 +/-0.10	1.50 +/-0.10
E	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10	1.75 +/-0.10
F	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	3.50 +/-0.05	5.50 +/-0.10	5.50 +/-0.10	5.50 +/-0.10



Size	0201, 0402, 0603, 0805, 1206, 1210			1812
Reel size	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W ₁	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	178.0±0.10
N	60.0+1.0/-0	100.0±1.0	100±1.0	60.0+1.0/-0

Aillen[®] Multilayer Ceramic Capacitors

Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70% related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solder ability in case of shelf life extension is needed.
- (3) Don't open the tape until the parts are to be used, use the chips within 3 months after the tape is opened.
- (4) For product of high dielectric constant (Class2&3, characteristics B/W & Y), the Electro static capacity changes with the passage of time due to the inherent characteristics of ceramic dielectric materials. The changed capacity reverts to nominal at the temperature it reaches during the soldering process.

Cautions:

- a. The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solder ability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- b. In corrosive atmosphere, solder ability might be degraded, and silver migration might occur to cause low reliability.
- c. Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sun light, the solder ability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N₂ within oven are recommended.

